



Properties and Test Method	Unit	A1	A2	Ultrasil VN3
Specific Surface Area (CTAB)	m ² /gr	167	167	165-170
Loss on drying (2 h 105°c)	%	4.8	4.8	Max 6
pH value 5% in water ISO787-9	-	6.3	6.3	6-7.5
Electrical Conductivity (4%) ISO787-14	μS/cm	1050	1050	Max 1300
SiO ₂ content	%	98	98	Min 97
Fe Content	ppm	150	150	Max 400
Product shape	-	Powder	Granule	Granule